



# RA6-235SD (6V235Ah)

RA6-235SD is AGM Deep cycle battery with 10 years floating design life, specially designed for frequent cyclic discharge usage. By using strong grid and specific paste plate, it makes battery have 30% more cyclic life time than standby series. It is applicable for solar energy system, golf cart, electric wheelchair, etc..



## Specification

Cells Per Unit	3
Voltage Per Unit	6
Capacity	235Ah@20hr-rate to 1.75V per cell @25°C
Weight	Approx. 32.0 Kg
Max. Discharge Current	2350 A (5 sec)
Internal Resistance	Approx. 1.7 mΩ
Operating Temperature Range	Discharge: -20°C~60°C Charge: 0°C~50°C Storage: -20°C~60°C
Normal Operating Temperature Range	25°C±5°C
Float Charging Voltage	6.8 to 6.9 VDC/unit Average at 25°C
Recommended Maximum Charging Current Limit	67.5A
Equalization and Cycle Service	7.3 to 7.4 VDC/unit Average at 25°C
Self Discharge	RITAR Valve Regulated Lead Acid (VRLA) batteries can be stored for more than 6 months at 25°C. Self-discharge ratio less than 3% per month at 25°C. Please charge batteries before using.
Terminal	Terminal F14
Container Material	A.B.S. (UL94-HB) , Flammability resistance of UL94-V1 can be available upon request.



MH28539




G4M20206-0910-E-16




ISO9001:2000 Certificate

## Dimensions

Unit: mm Dimension:243 (L)×187.5(W)×275(H)



Terminal F14



### Constant Current Discharge Characteristics: A (25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
4.80V	613.3	459.4	387.8	248.4	146.3	87.51	60.49	49.57	40.58	27.95	23.63	13.00
5.00V	595.5	437.1	379.8	244.3	145.6	86.85	60.26	49.34	40.34	27.72	23.40	12.76
5.10V	577.9	421.7	373.9	242.2	144.2	86.20	59.79	49.11	40.10	27.49	23.18	12.52
5.25V	518.9	389.1	356.0	236.1	142.9	85.54	59.56	48.65	39.62	27.27	22.95	12.29
5.40V	468.4	354.8	328.1	225.7	139.5	84.00	57.94	47.51	38.90	26.81	22.72	12.05
5.55V	399.9	317.1	294.3	211.5	132.5	80.27	55.39	45.21	37.23	25.68	22.04	11.34

### Constant Power Discharge Characteristics: W (25°C)

F.V/Time	5MIN	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
4.80V	3172	2446	2133	1416	845.0	515.7	359.9	295.4	242.0	166.9	141.2	77.92
5.00V	3109	2371	2099	1399	843.0	513.0	360.0	295.1	241.4	166.1	140.3	76.57
5.10V	3074	2309	2075	1389	836.5	509.9	358.5	294.4	240.6	165.0	139.1	75.15
5.25V	2798	2150	1979	1356	828.9	506.2	357.1	291.7	237.7	163.6	137.7	73.73
5.40V	2548	1982	1829	1300	813.6	499.8	347.3	285.0	233.4	160.9	136.3	72.31
5.55V	2238	1792	1647	1221	778.8	481.2	332.3	271.3	223.4	154.1	132.2	68.06


All mentioned values are average values.

# RA6-235SD


6V235Ah




## Life characteristics of cyclic use




## Storage characteristic



## Charge characteristic curve for cyclic use



## Discharge characteristic curve



## Capacity Factors With Different Temperature

Battery Type		-20°C	-10°C	0°C	5°C	10°C	20°C	25°C	30°C	40°C	45°C
GEL Battery	6V&12V	50%	70%	83%	85%	90%	98%	100%	102%	104%	105%
	2V	60%	75%	85%	88%	92%	99%	100%	103%	105%	106%
AGM Battery	6V&12V	46%	66%	76%	83%	90%	98%	100%	103%	107%	109%
	2V	55%	70%	80%	85%	92%	99%	100%	104%	108%	110%

## Discharge Current VS. Discharge Voltage

Final Discharge Voltage V/cell	1.75V	1.70V	1.60V
Discharge Current (A)	(A) ≤ 0.2C	0.2C < (A) < 1.0C	(A) ≥ 1.0C

## Maintenance & Cautions

<b>Cycle service</b>
※ Avoid battery over discharge, especially battery series connection use.
※ Charged with recommend voltage, ensure battery can be full recharged.
In general, recharge capacity should be 1.1-1.15 times discharge capacity.
※ Effect of temperature on cycle charge voltage: -4mV/°C/Cell.
※ There are a number of factors that will affect the length of cyclic service.
The most significant are depth of discharge, ambient temperature, discharge rate, and the manner in which the battery is recharged.
Generally speaking, the most important factors is depth of discharge.

**Charge the batteries at least once every six months, if they are stored at 25°C.**

### Charging Method:

Constant Voltage	-0.2Cx2h+2.4~2.45V/Cellx24h, Max. Current 0.3CA
Constant Current	-0.2Cx2h+0.1CAx12h
Fast	-0.2Cx2h+0.3CAx4.0h